

**POSE BRIQUES MORTAR - formulated for Masonry Clay Block Construction**

Ready mixed mortar for thin joint construction with Bouyer Leroux clay blocks.

This is a proprietary mortar for the Bouyer Leroux BioBric and BGV ranges.

Composition: hydraulic binders, silica sands, water retainer, resin and setting control agent.

**Packing:** 25kg bags

**Storage:** keep dry

**Shelf life:** 8-12 months if properly stored.

**Bulk density:** 1350g per litre

**Granulometry:** <1mm

**pH:** 12.5

**Water retention:** 93%

**Bonding strength:** 0.5MPa

**Compressive strength (28 days):** M 10 (EN/BS 998.1)

**Mixing:** In adequate container with already some water in it, add the mortar and whisk (slowly to start with). Keep adding water and whisking until a paste consistency is achieved. Total water addition about 40% (10 litres per 25 kg. bag).

Consumption per 25kg bag	Biobric 37.5	8.6m <sup>2</sup>
	Biobric 30	11m <sup>2</sup>
	B G V	16.6m <sup>2</sup>

**Application:** use specially designed mortar rollers

**NOTE:** once mixed, use within 15 minutes.

**For further Guidance, contact your St Astier Distributor.**

Copyright © 2016 CESA, Chaux et Enduits de St Astier

