



SAINT-ASTIER

LIME, LIFELONG EXCELLENCE

TRADIBLANC

A multi use Natural Lime Binder

Saint Astier Natural Hydraulic Limes (NHL)

For building mortars, roofing, chimneys, floor tiling. Based on St. Astier natural hydraulic lime with addition of white cement and additives for highly workable and breathable mortars. Similar to HOURDEX but white in colour for better sand colour reproduction.

Technical data	POWDER	Test std	MORTAR Mix ratio 1:3	Test std
Dry Density	800 g.l. +/- 10%	BS459	>1425g.l.>+/- 25g 1650g.l wet +/- 50g	EN1015-11 EN1015-6
Whiteness Y	70 +	NFX08.012		
Workability			210mm +/- 10mm	EN1015-3
Water retention			81% +/- 3%	CSTB 2669-4
Compressive strength 24h 7 days 28 days			1.5 N.mm ² (minimum) 4-5 N.mm ² (minimum) 6-7 N.mm ² (minimum)	BS998.2 BS998.2 BS998.2
Thermal conductivity			0.540 W/m.K	EN 1745
Vapour permeability			1.60.10 ⁻⁹ kg/m ² sPa (0.77g x m ² x h x mmHg)	EN 1015.19
Elasticity moduli			7000 – 9000 MPa	CSTB
Capillarity			0.75 g.min.	
Fire resistance			Class A (with silica or calcareous sands)	

CHAUX ET ENDUITS DE SAINT-ASTIER - FR 24110 SAINT-ASTIER - TEL FR: +33 5 53 45 46 70

Email: contact_export@saint-astier.com

WWW.STASTIER.CO.UK



SAINT-ASTIER

LIME, LIFELONG EXCELLENCE

Packing: 35kg. bags.

Pallets of 1 TON (40 bags).

Shelf life :12 months in dry and sealed conditions.

Mortar preparation: up to 5 minutes in conventional drum mixers.

Sand: clean, well graded 0-3mm (general). Lower or higher granulometries can be adopted. Avoid monogranular sands.

Adequately dampen materials or background if too dry or with high suction. Do not work in temperatures below 5°C or above 35°C.

The building materials or background should not be frosty or too hot or water saturated. Protect fresh mortars from frost, rain or strong direct sun. Storage: in dry store. Reseal open bags a.s.a.p

DOSAGES	TRADIBLANC	SAND (0-3mm)	By Volume
Bricks, blocks,			1:2.25 sand
floor tiling, roofing	1 bag (35kg)>	100 liters	1:2.25 sand
chimneys			1:2.25 sand



CHAUX ET ENDUITS DE SAINT-ASTIER - FR 24110 SAINT-ASTIER - TEL FR: +33 5 53 45 46 70

Email: contact_export@saint-astier.com

WWW.STASTIER.CO.UK